

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

**EP 0 721 776 A1**

(12)

**EUROPEAN PATENT APPLICATION**

(43) Date of publication:

17.07.1996 Bulletin 1996/29

(51) Int. Cl.<sup>6</sup>: **A61K 9/107**, A61K 47/34

(21) Application number: **96300196.1**

(22) Date of filing: **10.01.1996**

(84) Designated Contracting States:

**CH DE ES FR GB IT LI SE**

(30) Priority: **10.01.1995 JP 2210/95**

(71) Applicant: **RESEARCH DEVELOPMENT  
CORPORATION OF JAPAN**

**Kawaguchi-shi, Saitama-ken 332 (JP)**

(72) Inventors:

- **Sakurai, Yasuhisa**  
Tokyo (JP)
- **Okano, Teruo**  
Ichikawa-shi Chiba (JP)
- **Kataoka, Kazunori**  
Chiba (JP)

• **Yokoyama, Masayuki**

**Matsudo-shi Chiba (JP)**

• **Katayose, Satoshi**

**Kawasaki-shi Kanagawa (JP)**

• **Suwa, Satoru**

**Yamazaki Noda-shi Chiba (JP)**

• **Harada, Atsushi**

**1495 Matsudo Matsudo-shi Chiba (JP)**

(74) Representative: **Calamita, Roberto**

**Frank B. Dehn & Co.**

**Imperial House**

**15-19 Kingsway**

**London WC2B 6UZ (GB)**

(54) **Electrostatic bonding type macromolecular micelle drug carrier and drug carried thereon**

(57) The present invention provides an electrostatic bonding type macromolecular micell drug carrier comprising a block copolymer having a non-chargeable segment and a chargeable segment, for stably carrying a chargeable drug tending to be easily decomposed in vivo such as protein and DNA.

**EP 0 721 776 A1**

## Description

## FIELD OF THE INVENTION

The present invention relates to an electrostatic bonding type macromolecular micell drug carrier and drugs carried thereon. More particularly, the present invention relates to a novel macromolecular micell drug carrier of a chargeable drug such as protein and DNA, which is useful in areas such as a drug delivery system (DDS) which carries a drug to a permissive site in vivo and causes the drug to stably display the functions and effects thereof, drugs to be carried by such a carrier, and a method of carrying a drug on this carrier.

## PRIOR ART AND PROBLEMS

Macromolecular micell type drugs are attracting the general attention as a useful method for a drug delivery system (DDS), for example, and the present inventors have already proposed a macromolecular micell type drug which causes physical adsorption of a hydrophobic drug by a block copolymer comprising a hydrophilic segment and a hydrophobic segment.

The macromolecular micell type drug based on this physical adsorption is attracting the general attention because of a new structure and the possibility of using same in practice.



According to studies carried out by the present inventors, however, it is now clear that there still remain problems to be solved. More specifically, the macro-molecular micell drug based on this physical adsorption, although being very excellent as means to administer a hydrophobic drug, has a structure essentially characterized by physical adsorption of a hydrophobic drug by a block copolymer. There has therefore been a drawback that the method has been applicable only to drugs having a sufficient hydrophobicity.

Under such circumstances, there is a demand for achievement of novel technical means applicable in a wider range, which permits stable carrying of a drug irrespective of whether the drug is hydrophobic or hydrophilic.

## SUMMARY OF THE INVENTION

The present invention provides an electrostatic bonding type macromolecular micell drug carrier comprising a block copolymer having a non-chargeable segment and a chargeable segment, which solves the above-mentioned problems.

The present invention also provides embodiments of the above-mentioned carrier, in which the non-chargeable segment is polyethylene glycol; the chargeable segment is polyamino acid and the block copolymer is shown by any of the following formula (I) and (II);



(where,  $R_1$  is a hydrogen atom, a hydrocarbon group or a functional group or a functional group substituted hydrocarbon group;  $R_2$  is NH, CO or  $R_6(CH_2)_qR_7$ , where  $R_6$  indicates OCO, OCONH, NHCO, NHCOO, NHCONH, CONH or COO,  $R_7$  indicates NH or CO, and  $q$  indicates an integer of 1 or more;  $R_3$  is a carboxyl group, a carboxyl group substituted hydrocarbon group, an amino group substituted hydrocarbon group, a hydrazino group, substituted hydrocarbon group,  $(CH_2)_p-NHCNHNH_2$  group, where  $p$  indicates an integer of 1 or more, a nitrogen-containing heterocyclic group or nitrogen-containing heterocyclic group substituted hydrocarbon group;  $R_4$  is a hydrogen atom, a hydroxyl group or hydrocarbon group having any of CO, NH and O at the bonding terminal thereof;  $m$  is a number within a range of from 4 to

2,500; n is a number within a range of from 1 to 300; and x is a number within a range of from 0 to 300, provided that  $x < n$ ).

In addition, the present invention provides an electrostatic bonding type macromolecular micell carrier drug in which a drug is carried by the carrier as described above, and a carrying method for the manufacture thereof.

## BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 shows a spectral chart of  $^1\text{H-NMR}$  of PEG-P(Lys).

Fig. 2 shows a graph comparing measuring results of melting for cases with PEG-P(Lys)/DNA, free DNA and (Lys)/DNA.

## DETAILED DESCRIPTION OF THE INVENTION

The present invention as described above was developed as a result of studies carried out by the present inventors to overcome the problems in the conventional physical adsorption type macromolecular micell drug, and realizes a novel electrostatic bonding type macromolecular micell drug carrier essentially different from the physical adsorption type one, drugs carried by means thereof, and a method for carrying the drug.

In the electrostatic bonding type macromolecular micell carrier comprising a non-chargeable segment and a chargeable segment of the present invention as described above, various substances are applicable for the both segments within the scope of the present invention.

Applicable non-chargeable segments include, for example, polyalkylene glycol such as polyethylene glycol and polypropylene glycol, polyalkylene oxide, polysaccharide, polyacrylamide, poly-substituted acrylamide, polymethacrylamide, poly-substituted methacrylamide, polyvinylpyrrolidone, polyvinyl alcohol, polyacrylic acid ester, polymethacrylic acid ester, polyamino acid, and derivatives thereof.


Applicable chargeable segments include, for example, a polyamino acid having a chargeable side chain, or more specifically, polyaspartic acid, polyglutamic acid, polylysine, polyarginine, polyhistidine, or, polymalic acid, polyacrylic acid, polymethacrylic acid, polyethylene imine, polyvinylamine, polyacrylamine, polyvinyl imidazole, and derivatives thereof.

Substances applicable as a block copolymer of the present invention comprising these segments include;

Polyethylene glycol-polyaspartic acid block copolymer, polyethylene oxide-polyglutamic acid block copolymer, polyethylene glycol-polyarginine block copolymer, polyethylene glycol-polyhistidine block copolymer, polyethylene glycol-polyhistidine block copolymer, polyethylene glycol-polymethacrylic acid block copolymer, polyethylene-polyvinylamine block copolymer, polyethylene glycol-polyarylamine block copolymer, polyethylene oxide-polyaspartic acid block copolymer, polyethylene oxide-polyglutamic acid block copolymer, polyethylene oxide-polylysine block copolymer, polyethylene oxide-polyarylic acid copolymer, polyethylene oxide-polyvinyl imidazole block copolymer, polyacrylamide-polyaspartic acid block copolymer, polyacrylamide-polyhistidine block copolymer, polymethacrylamide-polyarylic acid block copolymer, polymethacrylamide-polyvinylamine block copolymer, polyvinylpyrrolidone-polyaspartic acid block copolymer, polyvinylalcohol-polyarginine block copolymer, polyacrylic acid ester-polyhistidine block copolymer, polymethacrylic acid ester-polyvinylamine block copolymer, and polymethacrylic acid-polyvinylimidazole block copolymer.


A representative structure of these block copolymers is one known as AB-type block copolymer.

More specifically, the following paragraph describes an AB-type block copolymer comprising a non-chargeable segment obtained from a polyethylene glycol derivative and polyaspartic acid as the chargeable segment:



This is a polyethylene glycol-poly( $\alpha$ ,  $\beta$ -aspartic acid) block copolymer comprising polyethylene glycol and poly( $\alpha$ ,  $\beta$ -aspartic acid), and is synthesized by copolymerizing  $\beta$ -benzyl-L-aspartate-N-carboxylic anhydride with poly-ethylene glycol which is a unilateral terminal aminogroup (molecular weight: 200 to 250,000) as the initiating agent. The molecular weight of the ( $\beta$ -benzyl, L-aspartate) portion of this polyethylene glycol ( $\beta$ -benzyl-L-aspartate) block copolymer is variable within a range of from about 205 to 62,000. Polyethylene glycol-poly( $\alpha$ ,  $\beta$ -aspartic acid) block copolymer is available by eliminating benzyl through application of an alkali treatment of this copolymer.

Polyethylene glycol-polylysine block copolymer, shown by the following formula, having a cationic segment as the block copolymer:



is synthesized through polymerization of  $\epsilon$ -carbobenzoxy-L-lysine anhydride with unilateral terminal primary amino-group polyethylene glycol (molecular weight: 200 to 250,000) as the initiating agent. Polyethylene glycol-polylysine block copolymer is available by subjecting the resultant polyethylene glycol-poly( $\epsilon$ -carbobenzoxy-L-lysine) block copolymer to a deprotecting reaction by the use of methane sulfonic acid.

In the present invention, while there is no particular limitation in the kind of drugs capable of being electrostatically carried in a macromolecular micell comprising a block copolymer as described above, applicable ones include macromolecular drugs such as peptide hormone, protein, DNA, RNA, and oligonucleotide and low molecular weight drugs having a chargeable functional group in molecules such as Adriamycin and Daranomycin.

When causing the macromolecular micell to carry any of these drugs, it is the basic practice to mix the block copolymer and the drug or a solution thereof. Various operations including dialysis, stirring, dilution, concentration, ultrasonication, temperature control, pH control and addition of an organic solvent may appropriately be adapted.

When including lysozyme, an antimicrobial enzyme, in the polyethylene glycol-poly( $\alpha$ ,  $\beta$ -aspartic acid) block copolymer shown above, lysozyme can be carried by mixing an aqueous solution of the copolymer with an aqueous solution of lysozyme under appropriate conditions including mixing ratio, ionic strength and pH.

Furthermore, when causing the polyethylene glycol-polylysine block copolymer described above to carry DNA, it is possible to conduct DNA to be carried by mixing an aqueous solution of the copolymer with an aqueous DNA solution under conditions including appropriate mixing ratio, ionic strength and pH.

As described above, according to the electrostatic bonding type macromolecular micell drug carrier and the carried drug using same of the present invention, a stable macromolecular micelle structure is available and chargeable substances such as protein and DNA can be efficiently incorporated into the internal nucleus thereof. It is thus decomposed in vivo into the body in a stable state.

The present invention is now described further in detail by means of examples. It is needless to mention that the present invention is not limited to these examples.

#### Example 1

Poly-L-lysine (degree of polymerization: 20, 0.43 mg) was dissolved into distilled water (1.0 ml), and a polyethylene glycol-polyaspartic acid block copolymer (PEG-P(Asp): molecular weight of PEG: 5,000, 23 aspartic acid residues per a chain of the block copolymer, 1.0 mg) was dissolved into distilled water (1.0 ml). Thereafter, these aqueous solutions were mixed. A weight average particle size of 41.3 nm and a number average particle size of 36.0 nm of the resultant mixture were measured by the method of dynamic light scattering. A zeta-potential of 0.643 and 0.569 mV for the entire surface of the mixture was measured by the method of trophoretic light scattering.

#### Example 2

Polyaspartic acid (degree of polymerization: 20, 0.32 mg) was dissolved into distilled water (1.0 ml), and polyethylene glycol-poly-L-lysine block copolymer PEG-P(Lys); molecular weight of PEG: 5,000, 20 L-lysine residues per chain of block copolymer, 1.0 mg) was dissolved into distilled water (1.0 ml). Thereafter, these aqueous solutions were mixed. A weight average particle size of 28.2 nm and a number average particle size of 42.8 nm of the resultant mixture were measured by the method of the dynamic light scattering.

#### Example 3

Chicken albumen lysozyme (1.0 mg) was dissolved into distilled water (1.0 ml), and PEG-P(Asp) (3.0 mg) was dissolved into distilled water (3.0 ml). Thereafter, these solutions were mixed. A weight average particle size of 24.9 nm and a number average particle size of 23.1 nm of the resultant mixture were measured by the method of the dynamic light scattering.



about 65°C in that place. In the sample in which PEG-P(Lys) was added up to 1.0 times to DNA, the increase in absorbance at about 45°C disappears, and only the increase in absorbance at about 65°C was observed, suggesting that the structure of DNA was completely stabilized. This confirmed that DNA and PEG-P(Lys) stoichiometrically form a complex.

Fig. 2 shows a case where the number of lysine residues of PEG-P(Lys) is equal to 0.50 times relative to DNA phosphate group, and cases with free DNA and P(Lys)/DNA.

Remarkable differences are observed also in Fig. 2.

#### Example 7

Poly-L-lysine (degree of polymerization: 20)(40 mg) was dissolved into 4 ml of the phosphate buffer solution, and polyethylene glycol-polyaspartic acid block copolymer(PEG-P(Asp);molecular weight of PEG: 5000, 20 aspartic acid residues per a chain of the block copolymer, 2, 32mg) was dissolved into 2.32 ml of the phosphate buffer solution.

Thereafter, these aqueous solutions were mixed. A weight average particle size of 44.7 nm and a number average particle size of 41.3nm of the resultant mixture were measured by the method of dynamic light scattering.

#### Example 8

Poly-L-lysine (degree of polymerization:20) was dissolved into 4 ml of the phosphate buffer solution, and PEG-P(Asp)(molecular weight of PEG:5000, 80 aspartic acid residues per a chain of the block copolymer 4.5mg) was dissolved into 4.5 ml of the phosphate buffer solution. Therefore, these aqueous solution were mixed. A weight average particle size of 43.6 nm and a number average particle size of 41.8 nm of the resultant mixture are measured by the method of dynamic light scattering.

#### Example 9



Polyethylene glycol-poly-L-lysine block copolymer(PEG-PLys:(molecular weight of PEG:500, 20 lysine residues per a chain of the block copolymer, 5mg) was dissolved into 1ml of the phosphate buffer solution, and polyethylene glycol-polyaspartic acid block copolymer(PEG-P(Asp); molecular weight of PEG: 5000, 20 aspartic acid residues per a chain of the block copolymer, 5mg, was dissolved into 1 ml of the phosphate buffer solution.

Thereafter, these aqueous solutions were mixed. A weight average particle size of 30.8 nm and a number average particle size of 28.8 nm of the resultant mixture were measured by the method of dynamic light scattering.

According to the present invention, as described above in detail, there are provided a carrier capable of stably carrying a drug under the effect of a macro molecular micell structure, and a drug carried by this carrier. It is possible to stably incorporate chargeable substances such as protein and DNA which tend to be easily decomposed in vivo.


#### Claims

1. An electrostatic bonding type macromolecular micell drug carrier comprising a block copolymer having a non-chargeable segment and a chargeable segment.
2. The carrier as claimed in Claim 1, wherein said non-chargeable segment is polyethylene glycol.
3. The carrier as claimed in Claim 1, wherein said chargeable segment is polyamino acid.
4. The carrier as claimed in Claim 1, wherein said block copolymer comprises one shown by the following formulae (I) and (II):



(where,  $R_1$  is a hydrogen atom, a hydrocarbon group or a functional group or a functional group substituted hydrocarbon group;  $R_2$  is NH, CO or  $R_6(CH_2)_qR_7$ , where  $R_6$  indicates OCO, OCONH, NHCO, NHCOO, NHCONH, CONH or COO,  $R_7$  indicates NH or CO, and  $q$  indicates an integer of 1 or more;  $R_3$  is a carboxyl group, a carboxyl group substituted hydrocarbon group, an amino group substituted hydrogen group, a hydrazino group substituted hydrocarbon group,  $(CH_2)_p-NHCNHNH_2$  group, where  $p$  indicates an integer of 1 or more, a nitrogen-containing heterocyclic group or a nitrogen-containing heterocyclic group substituted hydrocarbon group;  $R_4$  is a hydrogen atom, a hydroxyl group or a hydrocarbon group having any of CO, NH and O at the bonding terminal thereof;  $m$  is a number within a range of from 4 to 2,500;  $n$  is a number within a range of from 1 to 300; and  $x$  is a number within a range of from 0 to 300, provided that  $x < n$ ).

5. The carrier as claimed in Claim 4, wherein  $R_3$  is a group expressed by  $-COOH$ ,  $-CH_2COOH$ ,  $-(CH_2)_3NH_2$ ,  $-(CH_2)_2NHCNHNH_2$ , or a heterocyclic group shown by the following formula:



6. An electrostatic bonding type macromolecular micell carrier drug wherein a chargeable drug is carried by a carrier of any of Claims 1 to 5 having an opposite charge.
7. A method of carrying a chargeable drug on an electrostatic bonding type macromolecular micell carrier, which comprises the steps of mixing a chargeable drug with any of carriers of Claims 1 to 5 having an opposite charge, and causing said chargeable drug to be carried by electrostatic bonding within a macromolecular micell.

FIG. 1







FIG. 2



Application Number  
EP 96 30 0196



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 96 30 0196

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.6)
X	EP-A-0 583 955 (JAPAN RES DEV CORP) 23 February 1994	1-4	
A	* page 3, line 20-32; claim 1 * ---	4-7	
X	EP-A-0 397 307 (JAPAN RES DEV CORP) 14 November 1990	1-5	
A	* page 5; claims 1,2,4; example 1 * ---		
A	EP-A-0 456 106 (LEOPOLD PHARMA GMBH) 13 November 1991	1,6,7	
A	* page 3-4; claims 1,9 * ---		
A	EP-A-0 440 100 (HOFFMANN LA ROCHE) 7 August 1991	1,6,7	
	* page 2; claims 1,9,10 * -----		
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int.Cl.6)
Place of search THE HAGUE		Date of completion of the search 2 April 1996	Examiner Kanbier, D
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X : particularly relevant if taken alone  Y : particularly relevant if combined with another document of the same category  A : technological background  O : non-written disclosure  P : intermediate document</p> <p>T : theory or principle underlying the invention  E : earlier patent document, but published on, or after the filing date  D : document cited in the application  L : document cited for other reasons  .....  &amp; : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.82 (P04C01)